NOTES:

SUBSTRATE
 UV GRADE FUSED SILICA

2. COATING (APPLY ACROSS CLEAR APERTURE)

HARD COATED

PERFORMANCE SPECS:

T(AVG) = 90% FROM 558 - 850nm @ 45 ° AOI

R(AVG) = 98% FROM 350 - 544nm @ 45 ° AOI


T(ABS) = 50% @ 552nm @ 45 ° AOI




4. SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE

5. TRANSMITTED WAVEFRONT DISTORTION RMS @ 632.8nm ≤1λ

6. ROHS COMPLIANT





FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

		S1	S2		
	SHAPE	PLANO	PLANO		
	SURFACE QUALITY	60-40	60-40		
	CLEAR APERTURE	22.00 x 32.00	22.00 x 32.00		
	BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED		

]		G	Eamuna Optic	SS®
	THIRD ANGLE PROJECTION		TITLE	552nm, 25.2 X 35.6mm, DICHROIC FILTER	
)	ALL DIMS IN	mm	DWG NO	86334	SHEET 1 OF 1