## NOTES:

1. SUBSTRATE: Crystal Quartz and MgF2

2. COATING (APPLY ACROSS CLEAR APERTURE) \$1 & \$2: R(AVG) <1% @ 465 - 610nm

> DAMAGE THRESHOLD, PULSED: 2 J/cm² @ 8ns @ 1064nm CW: 500 kW/cm² @ 1064nm

3. SURFACE S1 TO BE PARALLEL TO SURFACE S2 TO WITHIN <1 ARCMIN


4. RETARDANCE:  $\lambda/2 \pm \leq \lambda/100$ 


5. TRANSMITTED WAVEFRONT: λ/4 @ 633nm

6. WAVELENGTH RANGE: 465 - 610 nm


7. TEMPERATURE COEFFICIENT: <1/500 λ/°C


8. Rohs Compliant











SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2	THIRD ANGLE PROJECTION		TITLE	30mm Dia, 465-610nm, λ/2 Achromatic Waveplate	
CLEAR APERTURE	Ø23.00	Ø23.00					
SURFACE QUALITY	20-10	20-10	ALL DIMS IN	mm	DWG NO	48498	SHEET 1 OF 1