NOTES:

1. SUBSTRATE: FUSED SILICA

2. COATING (APPLY ACROSS COATING APERTURE)

\$1 & \$2: 1064nm Laser AR Coating R(ABS) < 0.25% @ 1064nm @ 0° AOI

DAMAGE THRESHOLD,

PULSED: 15J/cm² @ 20ns, 20Hz @ 1064nm





4. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE

5. IMAGE ORIENTATION: BEAM DEVIATION

APPLY ARROW ON EDGE WITH PENCIL OR PERMANENT INK POINTING TOWARDS TITLTED SURFACE \$2

7. ROHS COMPLIANT





FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

	\$1	\$2	
SHAPE	PLANO	PLANO	
SURFACE QUALITY	20-10	20-10	
MIN CLEAR APERTURE	Ø11.25	Ø11.25	
MIN COATING APERTURE	Ø11.25	Ø11.25 0.5 RINGS	
POWER AT 632.8nm	0.5 RINGS		
IRREGULARITY AT 632.8nm	0.2 RINGS 0.2 RINGS		
BEVEL	PROTECTIVE AS NEEDED PROTECTIVE AS NEE		

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

		Edmund Optics ®		S®
THIRD ANGLE PROJECTION		TITLE	PRISM WEDGE FS 5 DEG 12.5mm 1064	Inm
ALL DIMS IN	mm	DWG NO	39129	SHEET 1 OF 1