NOTES:

1. SUBSTRATE:

FUSED SILICA (CORNING 7980)

- 2. S2 TO BE PARALLEL TO S1 TO WITHIN <3 ARCMINS
- 3. COATING (APPLY ACROSS COATING APERTURE)

S1 & S2: 266nm Laser AR Coating

R(ABS): Rabs <0.25% @ 532nm @ 0-45° AOI

DAMAGE THRESHOLD

PULSED: 10 J/cm² @ 532nm, 20ns, 20Hz





FINE GROUND SURFACE

5. CLEAR APERTURE AND COATING APERTURE ARE CENTERED ON SURFACE

6. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE

7. ROHS COMPLIANT





FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

| | \$1 | \$2 |
|-----------------------|---------------------|---------------------|
| SHAPE | PLANO | PLANO |
| SURFACE QUALITY | 10-5 | 10-5 |
| SURFACE FLATNESS | λ/10 | λ/10 |
| MINI COATING APERTURE | 68.58 | 68.58 |
| BEVEL | PROTECTED AS NEEDED | PROTECTED AS NEEDED |
| | | |

| | | | Edmund Optics | | |
|------------------------|-------------|-------|---|-------|-----------------|
| THIRD ANGLE PROJECTION | | TITLE | 76.2mm Dia., 12.7mm Thick, 532nm, λ/10 Fused Silica Window | | |
|) | ALL DIMS IN | mm | DWG NO | 20449 | SHEET 3 OF 4 |