NOTES: 1. SUBSTRATE: Sapphire (Al2O3) 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN ≤3.5 ARCMIN 3. COATING (APPLY ACROSS CLEAR APERTURE) Ø 100.00±0.10 2.00±0.05 \$1&\$2: Ravg ≤0.25% @ 880nm Ravg ≤1.25% @ 400 - 870nm Ravg ≤1.25% @ 890 - 1000nm 4. FINE GRIND SURFACE (ADD INK NOTE AS NEEDED) 5. ROHS COMPLIANT S1--S2 PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2	
SHAPE	PLANO	PLANO	
CLEAR APERTURE	Ø90.00	Ø 90.00	
SURFACE FLATNESS	2λ (typical)	2λ (typical)	
SURFACE QUALITY	80-50	80-50	
BIREFRINGENCE	0.008	0.008	
BEVEL	PROTECTED AS NEEDED	PROTECTED AS NEEDED	

			Edmund Optics®			
	THIRD ANGLE PROJECTION	THIRD ANGLE TITLE 100mm Dia., 2mm Thick, VIS-NIR AR Coated Sapphire Window		ated,		
_	ALL DIMS IN	mm	DWG NO	24172	SHEET 1 OF 3	