NOTES:

1. SUBSTRATE:

FUSED SILICA

2. SUFRACE S2 TO BE PARALLEL TO S1 TO WITHIN <3 ARCMIN

3. COATING (APPLY ACROSS CLEAR APERTURE)

S1: R(abs): >99% @ 355nm T(abs): >95% @ 532nm


S2: R(abs): <0.5% @ 532nm

DAMAGE THRESHOLD, PULSED: \$1: 2.5 J/cm² @ 355nm, 20ns, 20Hz 5 J/cm² @ 532nm, 20ns, 20Hz

S2: 10 J/cm² @ 532nm, 20ns, 20Hz

4. FINE GRIND SURFACE

5. ROHS COMPLIANT



FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2		
SHAPE	PLANO	PLANO		
SURFACE QUALITY	10 - 5	COMMERCIAL POLISH		
CLEAR APERTURE	Ø 22.86	N/A		
SURFACE FLATNESS	λ/10	N/A		
BEVEL	PROTECTED AS NEEDED	PROTECTED AS NEEDED		

			Edmund Optics ®		
	THIRD ANGLE PROJECTION 25.4mm Dia., 532nm T, 355nm R 45° Thin Harmonic Separator		hin		
)	ALL DIMS IN	mm	DWG NO	29043	SHEET 62 OF 86